What is claimed is:

- 1. A polymer obtainable by free-radical polymerization of
  - a) 30 to 99% by weight of tert-butyl acrylate and/or tert-butyl methacrylate as monomer A,
  - b) 1 to 70% by weight of acrylic acid and/or methacrylic acid as monomer B and
  - c) 0 to 12% by weight of a free-radically copolymerizable monomer or a free-radically copolymerizable monomer mixture as monomer C, where at least one of the monomers C produces a homopolymer with a glass transition temperature of less than 30°C, with the proviso that the % by weight add up to 100, where the K value of the polymers is between 27 and 38, with the proviso that the polymerization is carried out in the presence of a regulator if the K value of the polymers is less than or equal to 35.

15

10

5

- 2. The polymer according to claim 1, obtainable by free-radical polymerization of
  - a) 60 to 80% by weight of monomer A,
  - b) 20 to 40% by weight of monomer B and
  - c) 0 to 12% by weight of monomer or monomer mixture C.

20

- 3. The polymer according to either of claims 1 and 2, where the amount of monomer C is less than 10% by weight.
- 4. The polymer according to one of claims 1 to 3, where the amount of monomer C is less than 3% by weight.
  - 5. The polymer according to one of claims 1 to 4, where the K value is in the range from 29 to 35.
- The polymer according to one of claims 1 to 5, where the K value is in the range from 30 to 34.
  - 7. The polymer according to one of claims 1 to 6, where the carboxylate groups are partially or completely neutralized.

35

8. The polymer according to one of claims 1 to 7, where monomer A is tert-butyl acrylate, monomer B is methacrylic acid and monomer C is ethyl acrylate.

5

20

- 9. A process for the preparation of the polymers according to one of claims 1 to 8, which comprises free-radically polymerizing monomer A, monomer B and monomer or monomer mixture C, where the K value of the polymers is between 27 and 38, with the proviso that the polymerization is carried out in the presence of a regulator if the K value of the polymers is less than or equal to 35.
- 10. The use of the polymers according to one of claims 1 to 8 as film former.
- 11. The use of the polymers according to one of claims 1 to 8 in cosmeticpreparations, in particular in hair cosmetic preparations.
  - 12. The use of the polymers according to one of claims 1 to 8 in preparations for oral care and dental care.
- 15 13. A film former comprising at least one of the polymers according to one of claims 1 to 8.
  - 14. A cosmetic preparation comprising at least one of the polymers according to one of claims 1 to 8.
  - 15. A preparation for oral care and dental care comprising at least one of the polymers according to one of claims 1 to 8.